



# DARE TO DIY DIFFERENTLY

**Liquid Rubber EPDM & TPO Primer** is the ideal solution for bonding our coatings and is used to increase the bond strength on EPDM and aged or properly prepared TPO surfaces.

Our EPDM & TPO Primer is an Acrylic Emulsion which resists plasticizer migration and has good peel strength and shear resistance.

It is used to prime EPDM & TPO membranes to improve adhesion. Note that newer TPO membranes should be sanded thoroughly to roughen the surface with 120 grit sandpaper.



## LIQUID RUBBER EPDM & TPO PRIMER PERFORMANCE FEATURES

- Provides Superior Bond to EPDM/TPO Surfaces
- No VOC's & No Harmful Odors
- Cleans Up With Soap & Water
- Water Based
- Flexible When Cured
- Non-Flammable



## APPLICATION EQUIPMENT

**Liquid Rubber EPDM & TPO Primer** is applied either by brush, roller, or airless spray application. This primer will require one generous coat with the goal of maximizing adhesion to the existing EPDM roof membrane. The recommended coating thickness of the Primer is between 4-5 mils DFT (.01 mm) (175-200 ft<sup>2</sup>/gal). For best results, primer should be applied to a dry surface that is free of dirt, dust, debris, oil, grease, silicone, or any other contaminants that would prevent adhesion. Application within 24 hours of rain is not recommended. Primer will remain very sticky once dried, so be sure to work in manageable sections

**Refer to application guidelines for more information.**

Can be sprayed using a light industrial paint sprayer suitable for primers. 0.515-0.519 spray tip.

+1 855-592-1049 | [support@shopliquidrubber.com](mailto:support@shopliquidrubber.com) | [shopliquidrubber.com](http://shopliquidrubber.com)

The information contained herein is the best available to Liquid Rubber Canada Inc. and its affiliated companies relating to Liquid Rubber products and the use of Liquid Rubber products. It is based on tests believed to be reliable. There is no warranty expressed or implied in association with product use. Liquid Rubber Canada Inc. assumes no liability for any damages incurred in association with the use of Liquid Rubber Canada Inc. products. Information is subject to change without notice.



## DRYING TIME

Curing time will vary depending on temperature and relative humidity. **Liquid Rubber EPDM & TPO Primer** will be dry to the touch and will be ready for coating within 1-2 hours at 25°C (50% RH). The primer will remain very sticky after it dries, apply a topcoat as soon as possible after it has dried to the touch and is uniform in color, to prevent contamination of the primed surface.



## SUITABLE APPLICATIONS INCLUDE BUT ARE NOT LIMITED TO

- EPDM/TPO RV Roofs & Flat Roofs
- EPDM Pond Liners



## PHYSICAL PROPERTIES

Color (Liquid)	White (dries clear)
PH Value	7.0 - 9.0
% of solids	54 – 60%
Viscosity CPS @ 24°C	1000 - 3500
Flexibility	Flexible when Cured

Water Resistance	Fair
Flammability	Not Flammable
Shear @ 40°C (1"x1"x1000g)	60 min. (minimum)
Storage	10 – 30°C (50 - 86°F)
Freeze / Thaw Stable	Do not allow to freeze

## LIMITATIONS & WARRANTY

- Do not apply to dirty or contaminated surfaces
- Avoid contact with solvents or solvent type adhesives
- Will not bond to silicone
- Do not apply below 10°C/50°F
- Do not apply over coal tar

## PACKAGING

- 18.9 L (5 Gal.) Pails
- 3.78 L (1 Gal.) Cans
- 946 ml (1 Quart) Cans