



DARE TO DIY DIFFERENTLY

Liquid Rubber Geo-Textile Fabric is a stitch bonded polyester fabric and is one of the strongest materials available to the coatings industry for use as reinforcement in cold process waterproofing.

Stitch bonding offers an unusual combination of high strength properties with good elongation for excellent thermal stress force accommodations.



LIQUID RUBBER GEO-TEXTILE PERFORMANCE FEATURES

- Stitch Bonded For Superior Strength
- Conforms to Odd Shaped Surfaces
- Quick & Easy Application
- Up to 65% Elongation
- Reinforces Areas to Prevent Cracking
- Bridges Over Cracks, Seams, & Transitions



APPLICATION

Liquid Rubber Geo-Textile reinforcing fabric is installed over seams, cracks, around protrusions, and anywhere else movement is anticipated, using the 3-Course-Method. Apply a generous coat of your selected Liquid Rubber coating or primer, embed the fabric into the coating or primer while it is still wet, but before skinning takes place. Be sure there are no wrinkles in the fabric, and it sits flush on the surface. Then coat over the fabric with an additional generous coat in such a way as to completely impregnate the fabric. Once these areas are dry, apply additional coats over the entire areas until the proper coverage is reached.

+1 855-592-1049 | support@shopliquidrubber.com | shopliquidrubber.com

The information contained herein is the best available to Liquid Rubber Canada Inc. and its affiliated companies relating to Liquid Rubber products and the use of Liquid Rubber products. It is based on tests believed to be reliable. There is no warranty expressed or implied in association with product use. Liquid Rubber Canada Inc. assumes no liability for any damages incurred in association with the use of Liquid Rubber Canada Inc. products. Information is subject to change without notice.



DRYING TIME

At 25°C and 50% relative humidity, **Liquid Rubber Geo-textile** details fully cure in 24 hours. Curing time increases with thickness, in colder temperatures or higher humidity so environmental conditions must be considered before application.



SUITABLE APPLICATIONS INCLUDE BUT ARE NOT LIMITED TO

- Decks & Patios
- RV Roofs & Mobile Homes
- Flat & Sloped Roofs
- Gutters & Flashing
- Ponds
- AC Units, Skylights & Vents
- Balconies



PHYSICAL PROPERTIES

4-inch-Wide Geotextile

Weight	3 oz./sq. yd.
Tensile (ASTM D1682)	57.1 lbs.
Elongation (ASTM D1682)	61.65%
Mullen Burst (ASTM D3786)	176.8 lbs.
Tear (ASTM D1117)	16.1 lbs.

40-Inch-Wide Geo-textile

Weight	2.9 oz./sq. yd.
Tensile (ASTM D1682)	41 lbs.
Elongation (ASTM D1682)	25.8%
Mullen Burst (ASTM D3786)	127 lbs.
Tear (ASTM D1117)	14.2 lbs.

LIMITATIONS & WARRANTY

- Do not apply to dirty or contaminated surfaces
- Do not apply below 10°C/50°F
- Avoid contact with solvents and solvent type adhesives
- Do not apply over coal tar

PACKAGING

- 4-inch x 160 ft. Roll
- 4-inch x 300 ft. Roll
- 40-inch x 50 ft Roll
- 40-inch x 324 ft. Roll