



DARE TO DIY DIFFERENTLY

Liquid Rubber RV Lap Sealant is a one part, moisture cure sealant formulated to self-level and fill horizontal joints and crevices. It can also be used as a coating or for potting and encapsulating applications.

Liquid Rubber RV Lap Sealant contains no solvents, is nonflammable and VOC compliant. Offers excellent adhesion to clean substrates which allows it to be used without a primer in most circumstances.



LIQUID RUBBER SELF LEVELING LAP SEALANT PERFORMANCE FEATURES

- Paintable After 24 hrs.
- 100% Solids, Will Not Shrink
- No Solvents or Isocyanates
- Can Be Used For Coating, Potting & Encapsulating
- Easy to Dispense & Tool
- Resists UV & Weathering
- Low Odor, Eco-Friendly Formulation
- Adheres & Cures to Damp Surfaces



APPLICATION EQUIPMENT

Liquid Rubber RV Lap Sealant is applied using a standard caulking gun, and it requires no mixing or additives. Tooling, if necessary, should be done before skinning takes place. In applications where partial or total confinement of sealant is prevalent, the time required for proper cure is generally lengthened by the degree of confinement. Wet adhesive can be cleaned with alcohol. **DO NOT USE** petroleum-based solvents.

Suitable Substrates – Fiberglass, Aluminum, Galvanized Metal, EPDM, PVC & other Plastics



DRYING TIME

At 25°C and 50% relative humidity, **Liquid Rubber RV Lap Sealant** is paintable after 24 hours. Strength will start to develop immediately and continue increasing for 7 days after application. Higher temperature and higher humidity will accelerate skin & cure time. Cold temperatures and low humidity will slow down skin & cure time.



SUITABLE APPLICATIONS INCLUDE

- RV & Trailer Roofs
- Roofing Applications



PHYSICAL PROPERTIES

Color (Paste)	White
Modulus 100% (ASTM D412)	0.50 Mpa
Tensile Strength (ASTM D412)	1.33 Mpa
Elongation at Break (ASTM D412)	300 %
Lap Shear (ASTM D412)	130 psi

QUV Testing (ASTM G26)	Pass (4000 hrs.)
Service Temperature	-45.5°C to 104°C
Skin Formation Time	45 mins @ 25°C - 50% RH
Meets & Exceeds	ASTM C920, Cal. Prop 65
VOC Compliant (ASTM D 2369)	16 Grams per Liter

LIMITATIONS & WARRANTY

- Do not apply to dirty or contaminated surfaces
- Do not apply below 10°C/50°F
Do not use on Olefins such as TPO, Polyethylene or Polypropylene prior to testing
- Do not apply over coal tar

PACKAGING

- 10.2 oz. Standard Caulking Tube